

SANAKRYL® antikor AY/DZD

Serial number 0908

Water-soluble base anticorrosive coating

Features:

SANAKRYL antikor AY/DZD is specially modified version of **SANAKRYL antikor AY** intended especially for industrial usage. **SANAKRYL antikor AY/DZD** is one component water-soluble coating based on styrene-acrylate dispersion, special anticorrosive pigments, fillers and additives. **SANAKRYL antikor AY/DZD** is specified by very good adhesion to metal surfaces, fast drying and hardening and by good anticorrosive features, especially in humid areas.

Usage:

SANAKRYL antikor AY/DZD is used especially for temporary anticorrosive protection of various metal surfaces (even cast iron). For top coating, **SANAKRYL mat PROFI**, **SANAKRYL lesk PROFI** or **SANAKRYL antikor 1S** can be used.

Technical data:

Dry matter		min. 55 weight %, min. 43 volume %
pH		8,0–10,0
Consistency (F4)		50–120 s
Thickness		approx. 1,20 – 1,35 g/cm ³
Adhesion (grille)		0/0
Hardness:	1 den	10 %
Drying:	stage 1	30 minutes
	stage 5	50 minutes
Corrosion resistance	to 48 h salt mist (ISO 7253):	no peeling or corrosion, corrosion in cut 1–2 mm
	360 h condensation chamber (ISO 6270):	no peeling and corrosion, corrosion in cut 1–2 mm
Content of volatile organic compounds (VOC):		
Category/subcategory of product		A/i
Max. volume of VOC in the product		67,4 g/l
		0,051 kg/kg
TOC		0,0314 kg/kg

Consumption:

Consumption (thickness 25 µm):	approx. 77 g/m ²
Recommended thickness DFT (dry film):	25–65 µm

Color shade:

Black, red-brown, gray, other according to requirements of customer.

Packaging:

Returnable metal containers (approx. 800 kg), other according to requirements of customer

Storage:

In original unopened containers from 5 °C to 25 °C. It must not freeze!

Surface preparation:

Metal surfaces must be cleared of all impurities, non-adherent old coatings, corrosion and perfectly degreased (**ETERNAL odmašťovač**, or other suitable detergent). The coating is applied in surroundings temperature from 10 °C to 30 °C.

Application:

SANAKRYL antikor AY/DZD is intended especially for industrial usage. Its rheological features are suitable for application by dipping or spraying (air or airless), but it can be applied also by roller or brush.

Viscosity can be adjusted according to requirements of customer.

According to application technique the coating must be diluted:

1. Dipping: 25–50 s (F4), diluted with 0–5 % of water
2. Air spraying: 25–40 s (F4), diluted with 2–5 % of water
3. Brush, roller: diluted with 0–2 % of water
4. Airless spraying: original viscosity

The coating can be additionally dried (30–50 °C) if faster drying is needed.

Certification:

TZÚS Praha Authorized person number 204

Waste disposal:

Described on safety data sheet of the product.

Safety and hygiene at work:

SANAKRYL antikor AY/DZD is classified as harmful for the environment. It contains zinc phosphate. Harmful to aquatic life with long lasting effects. Avoid release to the environment. Dispose of contents/container by incineration in an incineration or disposal of hazardous waste in landfills for hazardous waste. The product is treated article, it contains biocidal agent. In contains reaction mixture CMIT/MIT (3:1) [Index number: 613-167-00-5]. May cause an allergic reaction. A safety data sheet is available on request. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. When following basic hygiene rules, it is not a health hazard. While working, it is suitable to use protective clothing, gloves and goggles. In case of contact with skin, wash with soap and water. In case of contact with eyes, rinse with water immediately. If the irritation does not stop, seek medical help. If swallowed, drink about 0,5 l of tepid water with 10 crushed charcoal tablets and seek medical help. Do not induce vomiting. Other details are described on safety data sheet of the product.